


p 703.358.2960  
 f 703.358.2961  
 Suite 600  
 1525 Wilson Blvd  
 Arlington VA 22209  
 www.aluminum.org



**ALLOY REGISTRATION ACCEPTANCE FORM  
 (CASTINGS)**

**DATE:** August 8, 2007

**TO:** Technical Committee on Product Standards  
 Technical Committee on Aluminum Casting Standards

**FROM:** Parvaneh Shafiee 

**ALLOY DESIGNATIONS:** 367.0, 367.1, 368.0, 368.1 Die Casting

**REGISTRANT:** Mercury Marine

**REGISTRATION DATE:** January 10, 2007

**REGISTERED COMPOSITION LIMITS:**

(Limits % Max, unless shown as a range)

Alloy Desig.	Former Desig.	Product <sup>5</sup> Form	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Sn	Others <sup>31</sup>		Aluminum	
													Each	Total <sup>3</sup>		
367.0	Mercalloy 367	Die Casting	8.5-9.5	0.25	0.25	0.25-0.35	0.30-0.50	-	-	0.10	0.20	-	38	0.05	0.15	Remainder
367.1 <sup>33</sup>	Mercalloy 367	Ingot	8.5-9.5	0.20	0.25	0.25-0.35	0.35-0.50	-	-	0.10	0.20	-	38	0.05	0.15	Remainder
368.0	Mercalloy 366	Die Casting	8.5-9.5	0.25	0.25	0.25-0.35	0.10-0.30	-	-	0.10	0.20	-	38	0.05	0.15	Remainder
368.1 <sup>33</sup>	Mercalloy 366	Ingot	8.5-9.5	0.20	0.25	0.25-0.35	0.15-0.30	-	-	0.10	0.20	-	38	0.05	0.15	Remainder

Unless specified below, for all referenced footnotes refer to the pink sheets.

New Footnote No. 38: Casting: 0.001% Max. P, 0.05-0.07 Sr.

Ingot: 0.001% Max. P; Sr range to be determined between producer and purchaser to allow for potential burn out at caster's facility.

cc: SC on Alloy and Temper Registration Mailing List  
 Dr. Raymond Donahue, Mercury Marine  
 Dr. Kevin Anderson, Mercury Marine  
 Michael Skillingberg  
 Peter Pollak  
 Revisions to the 2002 Edition of Pink Sheets  
 PN07-50 Project File  
 Project Completion File